

IN THE CLAIMS

1. (Currently Amended) A nonwoven layer for a filter for a vacuum cleaner bag, the non-woven layer being a spunbond nonwoven layer, ~~the non-woven layer having a first surface area and the non-woven layer comprising at least one region having a second surface area smaller than the first surface area,~~ wherein only a portion of said nonwoven layer ~~only said at least one region~~ is hot calendered so that an average pore size of the ~~at least one region~~ portion of the nonwoven layer is smaller than 50 μm , and fibers are bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the ~~region~~ portion is inhibited.

2. Cancelled.

3. (Previously Presented) The nonwoven layer according to claim 1, having a basis weight between 10 and 100 g/m^2 and wherein the spunbond fibers have an average fineness of 0.6-12 denier.

4. (Currently Amended) A nonwoven layer for a filter for a vacuum cleaner bag, the non-woven layer being a spunbond nonwoven layer, ~~the non-woven layer having a first surface area and the non-woven layer comprising at least one region having a second surface area smaller than the first surface area,~~ wherein ~~only said at least one region comprises an adhesive~~ is provided only at a portion of the nonwoven layer so that an average pore size of the ~~at least one region~~ portion of the nonwoven layer is smaller than 50 μm , and fibers are bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the ~~region~~ portion is inhibited.

5. (Previously Presented) The nonwoven layer according to claim 4, wherein the adhesive is a hotmelt, a cold glue, a dry-bond adhesive, a thermoplastic polymer, or mixtures thereof.

6. (Previously Presented) The nonwoven layer according to claim 5, wherein the amount of hotmelt is between 1 and 10 g/m².

7. Cancelled.

8. (Currently Amended) A composite layer for a filter for a vacuum cleaner bag, comprising:

a first nonwoven layer according to claim 4, and

a second nonwoven layer on top of the first nonwoven layer,

wherein the adhesive is located at an interface between the first nonwoven layer and the second nonwoven layer such that fibers of the first or the second nonwoven layer or the first and the second nonwoven layer are bonded together and a movement of the fibers in the first or second nonwoven layer or the first and second nonwoven layer relative to each other in a direction parallel to a surface of the first layer or the second layer is inhibited.

9. (Previously Presented) The composite layer according to claim 8, wherein the second nonwoven layer is a meltblown nonwoven layer, and wherein the adhesive is a hotmelt.

10. Cancelled.

11. (Currently Amended) A method for producing a nonwoven layer for a filter wherein the nonwoven layer is a spunbond nonwoven layer and ~~at least one region~~ a portion of the nonwoven layer has an average pore size smaller than 50 µm and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the ~~region~~ portion is inhibited, the method comprising the steps of:

treating only ~~the at least one region~~ portion of the nonwoven layer, the treated ~~region~~ portion having a smaller surface area than the filter such that the treated ~~region~~

portion has an average pore size smaller than 50 μm and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the ~~region~~ portion is inhibited, wherein the treating step comprises the steps of:

spraying of hotmelt, cold glue, dry-bond adhesive, thermoplastic polymer, or mixtures thereof, and

applying pressure to obtain a bonding of the fibers in the treated ~~region~~ portion.

12. (Currently Amended) A method for producing a nonwoven layer for a filter wherein the nonwoven layer is a spunbond nonwoven layer and ~~at least one region~~ a portion of the nonwoven layer has an average pore size smaller than 50 μm and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to a surface of the ~~region~~ portion is inhibited, the method comprising the step of:

treating only the portion ~~at least one region~~ of the nonwoven layer, the treated ~~region~~ portion having a smaller surface area than the filter such that the treated ~~region~~ portion has an average pore size smaller than 50 μm and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the ~~region~~ portion is inhibited, wherein the treating step comprises the step of hot calendering.

13. (Currently Amended) A method for producing a composite layer according to claim 8 comprising the steps of:

providing a first nonwoven layer,

applying an adhesive to the first nonwoven layer, and

providing a second nonwoven layer,

wherein an adhesive is located at an interface between the first nonwoven layer and the second nonwoven layer such that fibers of the first or the second nonwoven layer or the first and the second nonwoven layer are bonded together and a movement of the fibers in the first or second nonwoven layer or the first and the second nonwoven

layer relative to each other in a direction parallel to the surface of the layer is inhibited.

14. (Previously Presented) The method according to claim 13, further comprising the step of applying pressure to obtain a bonding of the fibers.

15. (Currently Amended) A filter medium for a vacuum cleaner bag, comprising a filter structure having a first surface area, the filter structure comprising a surface or an interface of the filter structure provided with a filter paper layer defining a first region having a second surface area smaller than the first surface area of the filter structure, the filter ~~structure~~ medium at the first region having reduced air permeability relative to a ~~second~~-region of the filter structure free of the filter paper layer.

16. (Previously Presented) The filter medium according to claim 15, wherein the filter paper layer is bonded to the filter structure.

17. (Previously Presented) The filter medium according to claim 16, wherein the filter paper layer is bonded using an adhesive wherein the adhesive is a hotmelt, a cold glue, a dry-bond adhesive, a thermoplastic polymer or mixtures thereof.

18. (Previously Presented) The filter medium according to claim 16, wherein the filter paper layer is bonded to the filter structure at discrete region.

19. (Previously Presented) The filter medium according to claim 15, wherein the filter structure comprises a nonwoven layer.

20. (Previously Presented) The filter medium according to one of the claim 15, wherein the filter structure comprises successively a spunbond, an air-laid, a spunbond, a melt-blown, and a spunbond layer.

21. (Currently Amended) The filter medium according to claim 15, wherein the filter

paper layer has an air permeability of at least ~~about~~ 250 l/m²/s.

22. (Currently Amended) A vacuum cleaner bag comprising a filter medium, the filter medium comprising a filter structure having a first surface area, wherein a surface or an interface of the filter structure is provided with a filter paper layer defining a ~~first~~ region having a second surface area smaller than the first surface area of the filter structure, the filter ~~structure~~ medium at the ~~first~~ region having reduced air permeability relative to a ~~second~~ region of the filter structure free of the filter paper layer.

23. (Currently Amended) The vacuum cleaner bag according to claim 22, wherein the filter paper layer is provided at a the region of a the surface of the filter structure such that, in operation, the region of the filter structure provided with the filter paper layer is exposed directly to an airflow entering the bag.

24. (Currently Amended) The vacuum ☐ cleaner bag according to claim 22 comprising two portions of filter medium wherein both portions are bonded together at an outer edge and wherein the first portion comprises an air inlet and the second portion comprises the filter paper layer at a region opposite to the air inlet.

25. (Previously Presented) The vacuum cleaner bag according to claim 22, wherein the filter paper layer is provided at the inner surface or the outer surface of the bag.

26. (Previously Presented) The nonwoven layer according to claim 4, wherein the adhesive is a pulverized polymer.

27. (Previously Presented) The method according to claim 11 wherein the polymer comprises a pulverized polymer.

28. (Currently Amended) The filter medium according to claim 15, wherein the filter paper layer has an air permeability of at least ~~about~~ 500 l/m²/s.

29. (Currently Amended) The filter medium according to claim 15, wherein the filter paper layer has an air permeability of at least ~~about~~ 600 l/m²/s.